

TECHNICAL DATA SHEET

Product:	Boric Acid Low Sulfate and Ultra Low Sulfate
Synonyms:	Boracic acid, Boronic Acid
CAS#	10043-35-3
Formula:	H ₃ BO ₃
Product Description:	Boric acid is a granular or powder, white crystalline solid with a slippery or soapy feel.
Packaging:	Boric acid is available in 25 kg (55 lb.) multi-wall paper or plastic bags, 1000 kg (2200 lb.) bulk bag packaging.
Applications:	<ul style="list-style-type: none">- Synthesis of various boron derivatives- Glass and ceramics- Textile fiberglass- Cellulose Insulation- Agriculture- Nuclear reactors- Lubrication- Pyrotechnics- Wood preservation- Insecticide- Pharmaceuticals- Adhesives
Precautions:	Boric acid is chemically stable under normal condition of storage, however, it is advised to store Boric acid under dry, cool and steady temperature conditions. During storage and transport avoid any wide variation in temperature. With temperature cycling and exposure to humid environment, Boric acid shows tendency for caking.

Typical properties of Boric Acid:

Property	Typical Value
Appearance	Granular slippery white powder
Bulk Density	50-60lb/ft ³ (Granular); 35-40lb/ ft ³ (Powder)
Angle of repose	32-34°
Solubility in water at 20°C, 50°C and 100°C	4.7%, 10.3% and 27.5% respectively
Solubility in Glycerol at 20°C	19.9%
Solubility in Ethylene Glycol at 25°C	13.6%
Solubility in Ethanol at 25°C	11.96

Chemical Analysis

Component	Unit	Specification Low Sulfate (min-max)	Typical Value Low Sulfate	Specification Ultra Low Sulfate (min-max)	Typical Value Ultra Low Sulfate
B ₂ O ₃	%	56.25-56.9	56.5	56.25-56.9	56.5
SO ₄	ppm	130 max.	105	12 max.	8
Fe	ppm	4 max.	3	3 max.	1
Cl	ppm	5 max.	5	3 max.	2
Water Insoluble	ppm	-	60	-	60
Purity	%	99.92-101.07%	100	99.92-101.07%	100

Dry Sieve Analysis

Size	US Mesh	Unit	Specification	Typical Value Low Sulfate	Specification	Typical Value Ultra Low Sulfate
(+)1.000 mm	+18	%	4 max.	1.0	4 max.	1.0
(-)0.063 mm	-230	%	4 max.	2.0	4 max.	2.0

This TDS is to provide all necessary information about the product that customers must be aware of. However, excepting the given specifications, other information provided in this TDS do not form part of any selling specification. Information contained in this TDS is correct to the best of ETIMINE's knowledge and understanding based on available information. However, no warranty of merchantability or any other warranty, expressed or implied, with respect to such information can be made, and no liability resulting from its use can be assumed. Users should make their own investigations to determine the suitability of the information for their particular purposes. In no event shall ETIMINE USA, INC be liable for any claims, losses, or damages of any third party or for lost profits or any special, indirect, incidental, consequential or exemplary damages, howsoever arising, even if ETIMINE USA has been advised of the possibility of such damages.